ISSN: 2582-4686 SJIF 2021-3.261, 2022-2.889, 2023-5.384, 2024-6.875 ResearchBib IF: 9.948 / 2024

THE MULTIDISCIPLINARY JOURNAL OF SCIENCE AND TECHNOLOGY

VOLUME-5, ISSUE-2

ARTIFICIAL OSTEOTROPIC SUBSTANCES FOR BONE DEFECT REPAIR IN DENTISTRY

Sh.F. Furkatov, A.I. Khazratov, U.J.Saykonov, A.M. Aytuganov

Samarkand State Medical University Department of Oral Surgery and Dental Implantology

Relevance. Synthetic osteotropic substances are increasingly being utilized to address bone deficiencies within dental practices. These materials are engineered to encourage bone formation and integration, providing essential support for dental implants and other restorative procedures. Their biocompatibility and ability to mimic the natural properties of bone make them valuable in overcoming challenges presented by defects or loss of bone tissue.

Researchers are focused on enhancing these synthetic materials to ensure optimal results in promoting osseointegration and facilitating healing in patients. Various formulations are being tested to improve strength, durability, and bioactivity, ensuring that they meet the specific needs of dental applications. By utilizing these innovative osteotropic materials, dental professionals can significantly improve patient outcomes, leading to more successful interventions and enhanced quality of life for those receiving dental care.

In summary, artificial osteotropic materials represent a promising solution for bone defect repair in the field of dentistry, enabling improved treatment strategies and patient care.

According to statistics, diseases accompanied by destructive changes in bone tissue (for example, benign tumors or radicular cysts) occupy one of the first places in the structure of maxillofacial defects.

Restoration of bone deficiency due to physiological regeneration is not always possible to the desired extent, moreover, it can take a long time. When a bone defect is infected, the bone tissue is in a state of hypoxia, which also slows down its regeneration. Local deficiency can cause long-term complications: deformities with further loss of bone tissue of the alveolar process, exposure of the roots of the teeth in the area of the defect, displacement of the position of the teeth, malocclusion, diseases of the temporomandibular joint. Also, local bone deficiency may lead to the impossibility of dental implantation, which will require additional surgical interventions and, as a result, an increase in the duration and cost of treatment. In this regard, along with the optimal choice of new surgical techniques, the choice of osteoplastic materials becomes relevant. It is generally recognized that osteoplasty opens up maximum possibilities for the rehabilitation of patients.

The purpose of the work: to identify the status of synthetic materials in the modern practice of dental surgeons based on the studied material.

Introduction. The modern range of bone materials for surgical dentistry is divided into several broad groups. Among them, the following stand out:

• Autogenic – bone material taken from the patient himself. This material is most effective, but it is not always possible to obtain it in the area of the defect, and removal from other anatomical areas can be traumatic for the patient.;

• Allogeneic – in this case, another person is the bone donor.;

• Xenogenic is one of the most common techniques that uses animal–derived material.;

ISSN: 2582-4686 SJIF 2021-3.261, 2022-2.889, 2023-5.384, 2024-6.875 ResearchBib IF: 9.948 / 2024

VOLUME-5, ISSUE-2

• Synthetic (or alloplastic) materials are artificially created materials. Osteoplastic materials belonging to these groups have a unique set of advantages and disadvantages, depending on the clinical requirements that were imposed on them.

Osteoplastic materials should be characterized by:

• osteogenicity — the ability to initiate bone tissue growth due to special viable osteogenic cells (auto-capacity);

Osteoinduction is the ability to stimulate tissue growth as a result of the material's action on the differentiation of mesenchymal stem cells (blood proteins, growth factors, and other bioactive components);

Osteoconduction is the ability of an osteoplastic material to play the role of a passive scaffold (matrix) for building new tissue, followed by resorption of the implanted graph.

There are also osteoneutral materials, which are inert materials used to fill space.In addition to these key properties, porosity (which ensures the germination of new bone tissue), biological and immunological compatibility with the recipient's body, infectious safety (sterility), economic and physical accessibility should be taken into account.

Synthetic materials. Despite their diverse chemical structure, origin, and production method, synthetic osteoplastic materials have a number of advantages. They never contain potentially dangerous residual proteins, do not contain dens or other pathogenic agents, allow modification of the rate of resorption and other characteristics at the production stage, and are easily standardized. Synthetic materials also virtually eliminate religious or ethical issues associated with the use of animal and cadaveric biomaterials.

Synthetic osteotropic materials in dentistry have a number of significant advantages: excellent biocompatibility, safety in use, accessibility, low probability of complications and economic efficiency. They began to be used to replace autografts along with biological osteotropic materials and were designed to increase biocompatibility, proliferation of new vessels and regeneration of bone tissue.

Modern selection of synthetic alloplastic materials:

• Inorganic substances: synthetic hydroxyapatite, tricalcium phosphate, calcium sulfate, bioactive glass, calcium carbonate;

• Organic substances: they are represented by polymers of animal and vegetable origin.

There are also two main types of hydroxyapatite preparations.:

• Resorbable hydroxyapatite. The most common is the OsteoGen representative. The material has a high rate of resorption in the body, low crystallinity and has a pronounced sorption activity.

• Nonresorbable hydroxyapatite – high temperature ceramics (PermaRidge, Interpore, OsteoGraft D, Capse). This material is obtained by heating to 800-1000 ° C, which leads to the formation of a stable condensation-crystalline form, poorly soluble in water.

Hydroxyapatite-based synthetic materials are most effectively used for temporary filling of the root canals of teeth, in apical and periodontal surgery. The advantage of hydroxyapatite is its complete non-immunogenicity and the ability to gradually resorption when interacting with living tissues. An important feature is its compatibility with mineralized body tissues. In the process of resorption, the breakdown products of calcium-phosphorous substances, that is, calcium and phosphorus ions, are metabolized naturally, without exceeding the norms of mineral content in urine and serum. Hydroxyapatite-based materials may contain elements of coral origin, which are polycrystalline ceramics based on aragonite. In addition, modern biocomposite materials based on hydroxyapatite

ISSN: 2582-4686 SJIF 2021-3.261, 2022-2.889, 2023-5.384, 2024-6.875 ResearchBib IF: 9.948 / 2024

THE MULTIDISCIPLINARY JOURNAL OF SCIENCE AND TECHNOLOGY

VOLUME-5, ISSUE-2

can include many additional components: antibiotics, regeneration stimulants, anti-inflammatory drugs, and antioxidants.

The inclusion of collagen in hydroxyapatite also proved to be very useful: being the main structural component of the intercellular matrix in natural bone tissue, collagen gives elasticity to the material and slows down the rate of its bioresorption. Collagen also has osteoinductive properties. However, collagen also has a certain antigenicity and toxicity, which can subsequently lead to the development of immunological reactions and rejection of osteotropic material.

History. Synthetic bone grafts are created in chemical laboratories using modern technologies. For more than 40 years, scientists have been researching the properties of various materials capable of creating a matrix for creating future bones in the human body without harming the patient. The first attempts to use synthetic hydroxyapatite were made back in the 70s of the last century. The first artificial hydroxyapatite was an inert, densely sintered ceramic and had no pronounced osteoinductivity; when used, a fibrous capsule was formed. Already in the early 80s, synthetic hydroxyapatite and tricalcium phosphate became available as bone substitutes in surgery and dentistry. In the course of further research, it was revealed that the different ratio of calcium and phosphorus in hydroxyapatite gave the material different variations in the substitution of calcium ions for water or hydrogen ions, which affected the possibility of fixation and subsequent retention of a blood clot on the surface of the material. At the same time, the osteotropic properties of hydroxyapatite consist in activating the processes of osteogenic cell division and differentiation, and the osseointegrative properties consist in forming a strong bond with bone due to chemical bonding, followed by resorption with replacement by newly formed bone. When hydroxyapatite was implanted, pronounced biological compatibility with the tissues of the host bed was observed: the inflammatory reaction, as well as systemic and local toxicity, were practically absent. Biodegradable hydroxyapatite stimulates the intake of calcium ions, which preserves the normal content of calcium ions and phosphates in the blood serum. During the resorption of hydroxyapatite, the formation of a fibrous capsule around the implant does not occur.

The development of synthetic osteotropic materials at the present stage. The desire to improve calcium phosphate ceramics has led to the creation of new compositions of polymers and calcium. Currently, collagen, polyglycolide and polylactide are used as the organic base of bioresorbtive polymers. In total, foreign authors classify modern composites into three groups with a peculiar chemical composition.:

• collagen + hydroxyapatite compositions;
• compositions of calcium phosphates + polymer;
• Polymer + ceramic compositions.

Collagen itself is an intercellular protein. It is characterized by high biocompatibility, the ability to biodegrade and activate the interaction between bone cells. Despite these undeniable advantages, the clinical use of collagen is associated with the usual risks of xenografts (infection). In this regard, research is underway in the field of alternative natural polymers such as vegetable alginate and animal chitosan. Osteoplastic materials containing artificial biodegradable polymers such as polylactide and polyglycolide are widely used in foreign surgical dentistry.

Conclusion. According to statistics, diseases accompanied by destructive changes in bone tissue occupy one of the first places in the structure of maxillofacial defects. Physiological regeneration may not always be able to replenish the required amount of bone tissue in the optimal time, which may later require additional treatment, both time-consuming and economically costly. In such cases, it is

ISSN: 2582-4686 SJIF 2021-3.261, 2022-2.889, 2023-5.384, 2024-6.875 ResearchBib IF: 9.948 / 2024

THE MULTIDISCIPLINARY JOURNAL OF SCIENCE AND TECHNOLOGY

VOLUME-5, ISSUE-2

advisable to use osteotropic materials. Modern surgery has at its disposal a wide range of osteotropic materials, varying in composition and properties. The dentist-surgeon selects the material based on the characteristics of the patient.

At the moment, synthetic osteotropic materials have received strong technological development: depending on their composition and manufacturing technology, they are able to exhibit various properties in the human body. Synthetic osteotropic materials have a number of significant advantages: excellent biocompatibility, safety in use, accessibility, low probability of complications and economic efficiency. They began to be used to replace autografts along with biological osteotropic materials and were designed to increase biocompatibility, proliferation of new vessels and regeneration of bone tissue.

Literature

1. Shokhjakhon, F., Jurabek, L., Bakhodir, O., & Aziz, M. (2024). ANTIBIOTIC PROPHYLAXIS IN DENTAL SURGERY. *SAMARALI TA'LIM VA BARQAROR INNOVATSIYALAR JURNALI*, *2*(3), 289-295.

2. Шохжахон, Ф. У. Р. К. А. Т. О. В., Исфандиёр, Х. А. Й. Д. А. Р. К. У. Л. О. В., НАРЗИЕВ, И., & Азимжон, А. Ъ. З. А. М. К. У. Л. О. В. (2024). ВОЗМОЖНОСТИ И ТРУДНОСТИ ИСКУССТВЕННОГО ИНТЕЛЛЕКТА, ПРИМЕНЯЕМОГО В СТОМАТОЛОГИИ. *SAMARALI TA'LIM VA BARQAROR INNOVATSIYALAR JURNALI*, *2*(3), 332-345.

3. Shokhjakhon, F., Zhurabek, L., Bakhodir, O., & Aziz, M. (2024). ON THE ISSUE OF BIOCOMPATIBILITY OF CERAMIC IMPLANTS IN THE PROVISION OF ORTHOPEDIC CARE. *SAMARALI TA'LIM VA BARQAROR INNOVATSIYALAR JURNALI*, *1*(6), 561-567.

4. Фуркатов, Ш., Хайдаркулов, И., Нарзиев, И., & Аъзамкулов, А. (2024). ВЛИЯНИЕ КУРЕНИЯ НА ЗДОРОВЬЕ ПАРОДОНТА: ОСВЕДОМЛЕННОСТЬ ПАЦИЕНТОВ МЕДИЦИНСКОГО КОЛЛЕДЖА АБУ АЛИ ИБН СИНО. *SAMARALI TA'LIM VA BARQAROR INNOVATSIYALAR JURNALI*, *1*(6), 574-581.

5. Фуркатов Ш. и др. ГНОЙНО-ВОСПАЛИТЕЛЬНЫЕ ЗАБОЛЕВАНИЯ ЧЕЛЮСТНО-ЛИЦЕВОЙ ОБЛАСТИ И ОПТИМАЛЬНЫЕ МЕТОДЫ ИХ ЛЕЧЕНИЯ //SAMARALI TA'LIM VA BARQAROR INNOVATSIYALAR JURNALI. – 2024. – Т. 1. – №. 6. – С. 568-573.

6. Furkatov S. F., Khazratov A. I. THE CONSEQUENCES OF THE DILIGENCE OF THE SLAVIC EMOLLIENT FOR REPARATION PROSTHESES ASEPT PARODONTAL //Молодежный инновационный вестник. – 2023. – Т. 12. – №. S2. – С. 467-470.

7. Rizaev, J. A., Khazratov, A. I., Furkatov Sh, F., Muxtorov, A. A., & Ziyadullaeva, M. S. (2023). Clinical and radiological characteristics of periodontic interweaves in patients with chew recessional. *European Journal of Interdisciplinary Research and Development*, *11*, 36-41.

8. Фуркатов Ш. Ф., Хазратов А. И. ПОСЛЕДСТВИЯ ПРИМЕНЕНИЯ СЛАВЯНСКОГО СМЯГЧАЮЩЕГО СРЕДСТВА ДЛЯ РЕПАРАЦИИ ПРОТЕЗОВ ПАРОДОНТАЛЬНОГО ОТДЕЛА //Молодежный инновационный вестник. – 2023. – Т. 12. – №. S2. – С. 467-470.

9. Фуркатов Ш. Ф., Хатамова М. А. ПРИМЕНЕНИЯ ВРЕМЕННЫХ НЕСЪЕМНЫХ ЗУБНЫХ ПРОТЕЗОВ ПРИ ДЕНТАЛЬНОЙ ИМПЛАНТАЦИИ //АКТУАЛЬНЫЕ ВОПРОСЫ СТОМАТОЛОГИИ. – 2023. – С. 814-820.

10. Исматов Ф. А., Мустафоев А. А., Фуркатов Ш. Ф. АНАЛИЗ ЭФФЕКТИВНОСТИ НЕСТЕРОИДНЫХ АНТИВОСПОЛИТЕЛЬНЫХ ПРЕПАРАТОВ ПРИ ИЗЛЕЧЕНЬЕ

ISSN: 2582-4686 SJIF 2021-3.261, 2022-2.889, 2023-5.384, 2024-6.875 ResearchBib IF: 9.948 / 2024

THE MULTIDISCIPLINARY JOURNAL OF SCIENCE AND TECHNOLOGY

VOLUME-5, ISSUE-2

ВЕРХНЕЧЕЛЮСТНОГО АЛЬВЕОЛИТА //THEORY AND ANALYTICAL ASPECTS OF RECENT RESEARCH. – 2023. – Т. 1. – №. 12. – С. 49-57.

11. Rizaev, J. A., Rustamova, D. A., Khazratov, A. I., & Furkatov, S. F. (2022). The need of patients with systemic vasculitis and coronavirus infection in the treatment of periodontal diseases. *Applied Information Aspects of Medicine (Prikladnye informacionnye aspekty mediciny)*, *25*(4), 40-45.

12. Ризаев Ж. А., Нарзиева Д. Б., Фуркатов Ш. Ф. РЕГИОНАРНАЯ ЛИМФОТРОПНАЯ ТЕРАПИЯ ПРИ ФУРУНКУЛАХ И КАРБУНКУЛАХ ЧЕЛЮСТНО-ЛИ-ЦЕВОЙ ОБЛАСТИ //ТОМ-1. – 2022. – С. 386.